
SARL AZHAR BOIS SAWN LOGS

01.01.2024

Main quality requirements of saw logs

Direct contact Europe:
Ph: +358 409 124446

1. The wood must be freshly sawn - prepared.

2. Maximum and minimum diameters

✓ Min. Diameter of lean meat under the skin 10 cm

✓ Max. Diameter of lean meat under the skin 60 cm

✓ Max. The diameter of the thicket under the bark is 60 cm

3. Lengths

✓ 3.3; 3.6; 4.2; 4.8; 5.1; 5.4; 6.0 + surface measurement 10 cm

✓ Max. Length 6.2 m (6.21 m – short)

✓ Min. Length 3.3 m (3.39 m – short)

4. Branches

✓ Max. the height of the branches from the surface of the log under the bark is 4 cm

✓ Max. diameter of the branches at the thickest point – 80 mm for Spruce, 100 mm for Pine

5. Bending

✓ Uniform – 1% is allowed for logs with a diameter of up to 16 cm

✓ Uniform – 1.5% is allowed for logs with a diameter over 16 cm

✓ Composite - not allowed

6. Compressed wood

✓ For spruce sawn logs, 50% of the working cylinder of the log is allowed* square.

✓ Pine logs are allowed.

7. Dryness, cracks

✓ Not allowed in log work cylinder.

Not allowed:

✓ Troupe

- ✓ Double top
 - ✓ Muddy
 - ✓ Burnt logs smeared with coal, soot and soot
 - ✓ Insect damage
 - ✓ Dry logs
 - ✓ Bruising
 - ✓ Metal
-